

Product Information





TECHNICAL DATA Tribrid® Polymer

Shrinkage % nil

Excellent Coherent Flow

Skinning Time23°C 50% R.H.25 minutesTack Free Time23°C 65% R.H.140 minutesFull Cure Time23°C 50% R.H.24hrs - 3mm

Curing system: Neutral Cure

Hardness – DIN 53505 60 Shore A

Tensile Strength – 290 N/cm² / 2.9 MPa

EN ISO 8339

Thermal Stability: -30°C to + 80°C

Elongation at Break -

DIN 53504 300%

Non toxic

EC1 Plus Certified

Chemical Resistance

Good: Water, seawater, aliphatic solvents, oils, greases diluted organic acids.

Moderate: Esters, Ketones, Aromatics, chlorine for swimming pools chlorinated solvents.

Limitations: Strong Acids and Alkalis

Dirt attachment: Practically none

Shelf Life: 18 months

All above tests according to ISO 11.600 20HM

ETAG 022 Annex E,B & Additional tests of Annex F. ISEGA Food Approval.

BT1 is the only scientifically developed Tribrid® polymer with unique resistance to mould and fungal infestation, thereby creating a much healthier environment.

Tested under MOD IOS 22196:2011, BT1 has been proven to reduce bacteria by up to 99.99% and is effective against a broad spectrum of microbes including MRSA, E. coli and Campylobacter.



Product Information









APPLICATIONS

- For all applications, including bathrooms, wet rooms, hospitals, clinics and all public health institutions, BT1 replaces: Wood and P.U. adhesives, silicone sealants, sanitary silicone sealants, acrylic sealants and butyl rubber sealants.
- As a universal adhesive BT1 bonds to most substrates including: woods, metals, brickwork, fibreglass, glass, ceramics, uPVC, concrete and most plastic, (except PP, PE and PTFE), even in wet conditions and doesn not attack synthetic material.
- On mirror applications apply in vertical strips (Not suitable for PP backed mirrors).
- BT1 can also be painted but must be fully cured and is usable with all common water-based paints (not suitable with Alkyd Paints). For best results prior testing is recommended.
- For application advice on powder coated substrates contact powder coating manufacturer.

DIRECTION FOR USE:

- Before use, ensure the cartridge has been stored at room temperature.
- Cut the Cartridge at the nose.
- Cut off nozzle at desired dimensions.
- Use a Skeleton or Powered Gun.
- Apply on a clean, degreased surface.
 Finish off the joints with MULTISOLVE.

BT1: DELIVERY FORM

- 290ml Cartridges.
- Colours Available: White.

C-Tec N.I. Limited, Unit 6 Ashtree Enterprise Park, Newry, Co. Down, Northern Ireland, BT34 1BY.
Tel: 028 3083 4892 Fax: 028 3026 4444
Email: info@ct1.com Web: www.ct1.com

All information, including illustrations, is believed to be reliable. Users however, should independently evaluate the suitability of each product for their application. C-TEC makes no warranties of the accuracy of completeness of the information, and disclaims any liability regarding its use. C-TEC only obligations are those in the standard terms and conditions of sale of this product, and in no case will C-TEC be liable for any incidental, indirect or consequential damages arising from the sale, resale, use or misuse of this product. (20200211)